


Formula Selection

Considerations for viewing color.

- Use daylight or corrected lighting.
- Practice good technique.




Technique – Step #1 Face Color Viewing:

1. 3M™ Sun Gun™ should be at a 65° angle to the car and close to the technicians left ear.
2. The technicians eyes should be at a 90° angle and perpendicular to the car at approximately 12" - 18" away.
3. When viewing spray out or variant swatch the technician should be at eye level focusing primarily at the bottom and center of the panel.

Formula Selection

Considerations for viewing color.

- Use daylight or corrected lighting.
- Practice good technique.



Technique – Step #1 Flip Color Viewing:

1. When viewing spray out or variant swatch the technician should be eye level focusing primarily at the bottom and center of the panel.
2. 3M™ Sun Gun™ should be at a 25° angle to the car and close to the technicians left ear.
3. The technician's eyes should be at 12 - 15° angle to the car and approximately 12" - 18" away.